



## Technical Data Sheet

# Tronox<sup>®</sup> 8951 SL

TRONOX<sup>®</sup> 8951SL is a high solids aqueous dispersion of rutile titanium dioxide pigment. It is formulated to retain good dispersion in the slurry and has enhanced calcium stability. No mercurial or formaldehyde releasing biocide is added. Coatings prepared with TRONOX<sup>®</sup> 8951SL have a clean tint tone and color.

### Applications

Paper Coating ■ Paperboard Coating ■ Paper Filling ■ Coated recycled board

### Typical Properties<sup>1</sup>

Solids content, %	71.5
Density, lbs/gal	18.0
pH	9.0
Viscosity, cps <sup>2</sup>	150

#### Specification

ASTM D476.....Type II

Acceptable for FDA food contact substance uses under the following sections:

21 CFR 176.170 Components of Paper and Paperboard in contact with aqueous and fatty food (Table 2, Conditions of use A-H)

21 CFR 176.180 Components of Paper and Paperboard in contact with dry food

<sup>1</sup>Typical properties not to be construed as specifications

<sup>2</sup>Brookfield, @ 100 rpm

#### Plant Locations:

Botlek, The Netherlands  
Mississippi, U.S  
Kwinana, Australia

#### Sales Offices:

Oklahoma City 1 800 654 3911  
Singapore +65 6255 0098  
Shanghai, China +86-21-6422-8955  
Perth, Australia +61 8 9411-1444  
Botlek, The Netherlands +31 181 246600

06/17

The information herein is believed to be reliable. However, no warranty, expressed or implied, is made as to its accuracy or completeness and none is made as to the merchantability of the material or its fitness for any purpose. The manufacturer shall not be liable for consequential damages or for damages to persons or property resulting from its use. Nothing herein shall be construed as a recommendation for use in violation of any patent.